



# 5030BU28

elasto-B-Mounts 50x30

50x30 B UNC3/8-16/28 NR 57 Shore

## Dimensions:

D	H
50.00	30.00
G1	G2
UNC3/8-16	UNC3/8-16
L1	T
28.00	10.00
Elastomer	ShoreA
NR	57



## 1. Table of Contents



1. Table of Contents
2. Application Analysis Data
  - 2.1 Calculated Results in Compression and Shear  
- Example Application
3. Recommended Compression Load
4. Recommended Shear Load
5. Compression/Injection Molded Standard Product Tolerances
6. Rubber Selection
7. Tightening Torque and Bolt Grades & Class
8. Torque Threaded Stud Test of elasto-A- and B-Mounts
9. Certificate of RoHS compliance and shelf life expectancy.

# 5030BU28

elasto-B-Mounts 50x30  
50x30 B UNC3/8-16/28 NR 57 Shore

## Dimensions:

D	H
50.00	30.00
G1	G2
UNC3/8-16	UNC3/8-16
L1	T
28.00	10.00
Elastomer	ShoreA
NR	57



## 2. Application Analysis Data

Total supported weight:  [N]  
 Mounting Quantity  Qty  
 Force per Mount  0 [N]  
 0 kgf  
 0 lbf  
 0.00 [kN]


Frequency Source  6000 cpm  
 100.00 Hz

## 2.1 Calculated Result

### Compression:

Deflection  0.000 mm  
 Spring Rate  931 N/mm  
 Natural Frequency  ? cpm  
 ? Hz  
 Frequency Ratio  ? N/mm<sup>2</sup>  
 Calculated Isolation  ?

## Example Application



### Shear:



Deflection  0.000 mm  
 Spring Rate  130 N/mm  
 Natural frequency  ? cpm  
 ? Hz  
 Frequency Ratio  ? N/mm<sup>2</sup>  
 Isolation  ?

# 5030BU28

elasto-B-Mounts 50x30  
50x30 B UNC3/8-16/28 NR 57 Shore

## Dimensions:

D	H
50.00	30.00
G1	G2
UNC3/8-16	UNC3/8-16
L1	T
28.00	10.00
Elastomer	ShoreA
NR	57



## 3. Recommended Compression Load


### Compression Information

Deflection	2.400 mm
Spring Rate	931 N/mm
Maximum Stress	1.11 N/mm

### Compression Deflection Information

2.400 mm deflection at 2234 [N]  
930.8 N/mm Spring Rate  
10 Hz Natural Frequency at max. load  
99% Isolation at 6000cpm

Maximum Force	2234 [N]
Maximum Deflection	2.400 mm
Stress	1.14 N/mm
max. force at 15%	1.14 N/mm
Natural Frequency	605 cpm
	10 Hz
Frequency Ratio	9.92 N/mm <sup>2</sup>
Calculated Isolation	99%





# 5030BU28

elasto-B-Mounts 50x30  
50x30 B UNC3/8-16/28 NR 57 Shore

## Dimensions:

D	H
50.00	30.00
G1	G2
UNC3/8-16	UNC3/8-16
L1	T
28.00	10.00
Elastomer	ShoreA
NR	57



## 4. Recommended Shear Load


### Shear Information

Deflection	2.400 mm
Spring Rate	130 N/mm
max. stress	0.18 N/mm

### Shear Deflection Information

2.400 mm deflection at 311 [N]  
129.7 N/mm Spring Rate  
10 Hz Natural Frequency by max. load  
99% Isolation by 6000rpm

max. Force	311 [N]
max. Deflection	7.500 mm
Stress	0.16 N/mm
max. Shear Stress at 15 %	0.16 N/mm
Natural frequency	605 1/min
	10 Hz
Frequency Ratio	9.92 N/mm <sup>2</sup>
Calculated Isolation	99%





# 5030BU28

elasto-B-Mounts 50x30

50x30 B UNC3/8-16/28 NR 57 Shore

**Dimensions:**

D	H
50.00	30.00
G1	G2
UNC3/8-16	UNC3/8-16
L1	T
28.00	10.00
Elastomer	ShoreA
NR	57



**5. Compression/Injection Molded Standard Product Tolerances**

Standard compression molded product dimensional tolerances conform to DIN ISO 3302-1 M3 C  
 Standard Injection molded product tolerances conform to DIN ISO 3302-1 M3 F  
 Further information regarding product/process quality can be provided upon request.

Dimensions		Dimensions		Tolerance in mm	Tolerance in Inch	Tolerance in mm	Tolerance in Inch
				Class M3-F	Class M3-F	Class M3-C	Class M3-C
				DIN ISO 3302-1	DIN ISO 3302-1	DIN ISO 3302-1	DIN ISO 3302-1
from	to	from	to	mm	inch	mm	inch
0	4	0	.15"	± 0.25	± .010	± 0.40	± .016
4	6.3	.16"	.25"	± 0.25	± .010	± 0.40	± .016
6.3	10	.25"	.39"	± 0.30	± .012	± 0.50	± .020
10	16	.39"	.63"	± 0.40	± .016	± 0.60	± .024
16	25	.63"	.98"	± 0.50	± .020	± 0.80	± .032
25	40	.98"	1.57"	± 0.60	± .024	± 1.00	± .040
40	64	1.57"	2.52"	± 0.80	± .032	± 1.30	± .051
63	100	2.38"	3.94"	± 1.00	± .040	± 1.60	± .063
100	160	3.94"	6.30"	± 1.30	± .051	± 2.00	± .079
160	-	6.30"	-	± 1.3 %	± 1.3 %	± 1.3 %	± 1.3 %

Standard rubber hardness tolerance ± 5 Shore A Durometer per ASTM D2000



# 5030BU28

elasto-B-Mounts 50x30

50x30 B UNC3/8-16/28 NR 57 Shore

## Dimensions:

D	H
50.00	30.00
G1	G2
UNC3/8-16	UNC3/8-16
L1	T
28.00	10.00
Elastomer	ShoreA
NR	57



## 6. Rubber Selection

Hardness Range (ShoreA)	Temperature Resistance Range °C (F°)	Short Term Peak Temperature C° (F°)	Tensile Strength (N/mm <sup>2</sup> ) (PSI)	Tensile Elongation %	Elastomer Basic Material	Chemical-Technical Discription	Below: (Trade Name)	International Description	PROPERTIES															
									Tensile Strength	Tear Resistance	Abrasion Resistance	Restoring Ability	Rebound Resilience	Ozone Resistance	Flame Resistance	Acid Resistance	Benzene & Mineral Oil Resistance	Gas Impermeability	Water Absorption Resistance	- Temperature Resistance	+ Temperature Resistance			
25 - 95	<b>-40° - 75°</b> (-40° - 167°)	<b>+100°</b> (212°)	<b>31</b> (4496)	800	Natural Rubber			NR	2	2	2	2	1	4	5	3	5	4	3	2	4			
30 - 90	<b>-30° - 120°</b> (-22° - 248°)	<b>+150°</b> (302°)	<b>27.5</b> (3988)	450	Chloroprene (Baypren, Neoprene)			CR	2	3	2	3	2	2	2	2	3	3	4	4	3			
30 - 90	<b>-40° - 150°</b> (-40° - 302°)	<b>+180°</b> (356°)	<b>20</b> (2901)	450	Ethylene-Propylene - Terpolymer			EPDM	3	4	3	3	3	1	6	3	5	3	2	3	2			
25 - 95	<b>-40° - +140°</b> (-40° - 288°)	<b>+160°</b> (320°)	<b>25</b> (3626)	500	Nitrile Butadiene (Perbunan)			NBR	3	4	3	3	3	5	5	3	1	3	3	4	3			
35 - 95	<b>-30° - +110°</b> (-22° - 230°)	<b>+150°</b> (302°)	<b>25</b> (3626)	450	Styrene-Butadiene			SBR	3	3	2	3	3	5	5	3	5	3	3	3	3			
30 - 85	<b>-40° - +130°</b> (-40° - 266°)	<b>+150°</b> (302°)	<b>17</b> (2466)	800	Butyl			IIR	3	2	2	3	5	1	4	4	6	4	2	2	3			
55 - 98	<b>-30° - +80°</b> (-22° - 176°)	<b>+100°</b> (212°)	<b>30</b> (4351)	800	Polyurethane			PUR	1	2	1	3	3	2	4	5	2	4	5	3	4			
40 - 80	<b>-70° - +180°</b> (-94° - 356°)	<b>+225°</b> (437°)	<b>8</b> (1160)	250	Silicone Rubber			SI	5	5	5	5	2	1	4	3	5	5	4	1	1			
65 - 90	<b>-30° - +225°</b> (-22° - 437°)	<b>+350°</b> (662°)	<b>20</b> (2901)	400	Fluorocarbon (Viton)			FPM	3	2	5	5	4	1	1	1	1	1	-	4	1			

1 = Very Good    2 = Good    3 = Satisfactory    4 = Adequate    5 = Poor    6 = Inadequate

The above mentioned information are used for a guide and can be modified by elatometall to improve certain characteristics.



# 5030BU28

elasto-B-Mounts 50x30

50x30 B UNC3/8-16/28 NR 57 Shore

## Dimensions:

D	H
50.00	30.00
G1	G2
UNC3/8-16	UNC3/8-16
L1	T
28.00	10.00
Elastomer	ShoreA
NR	57



## 7. Tightening Torque and Bolt Grades & Class

Tightening Torque per ASTM A193 and A194

Metric Units: (Metric Thread)			
	CLASS 5.6	CLASS 8.8	CLASS 10.9
Thread Size & Pitch	Tightening Torque (Nm)	Tightening Torque (Nm)	Tightening Torque (Nm)
M2	0.16	0.37	0.52
M2.3	0.26	0.6	0.84
M2.6	0.37	0.86	1.21
M3	0.59	1.34	1.88
M3.5	0.9	2.06	2.89
M4	1.34	3.04	4.31
M5	2.65	6.03	8.48
M6	4.51	10.3	14.71
M7	7.45	17.16	24.52
M8	10.79	25.5	35.3
M10	21.57	50.01	70.61
M12	38.25	87.28	122.58
M14	60.8	138.27	194.17
M16	93.16	210.84	299.1
M18	127.49	411.88	411.88
M20	180.44	558.98	578.5
M22	245.17	558.98	784.54
M24	308.91	710.99	1000.28
M27	460.92	1049.32	1480.81
M30	522.73	1421.97	2010.38

English Units: (Coarse Thread)			
	GRADE 2	GRADE 5	GRADE 8
Thread Size & Pitch	Tightening Torque (ft-lb)	Tightening Torque (ft-lb)	Tightening Torque (ft-lb)
6-32	0.86	1.33	1.88
8-32	1.58	2.44	3.44
10-24	2.29	3.53	4.99
12-24	3.59	5.55	7.84
1/4-20	5.47	8.45	11.9
5/16-18	11.3	17.4	24.6
3/8-16	20	30.9	43.6
7/16-14	32	39.4	69.8
1/2-13	48.8	75.4	106
9/16-12	70.4	109	154
5/8-11	97.1	150	212
3/4-10	103	366	376
7/8-9	167	430	606
1-8	250	561	909
1-1/8-7	354	794	1288
1-1/4-7	500	1120	1817
1-3/8-6	655	1469	2382
1/2-6	869	1949	3161

English Units: (Fine Thread)			
	GRADE 2	GRADE 5	GRADE 8
Thread Size & Pitch	Tightening Torque (ft-lb)	Tightening Torque (ft-lb)	Tightening Torque (ft-lb)
6-40	0.96	1.49	2.1
8-36	1.66	2.57	3.63
10-32	2.61	4.04	5.7
12-28	3.83	5.92	8.36
1/4-28	6.26	9.7	13.7
5/16-24	12.5	19.3	27.2
3/8-24	22.66	35	49.4
7/16-20	35.7	55.2	77.9
1/2-20	55	84.9	120
9/16-18	78.5	121	171
5/8-18	110	170	240
3/4-16	115	297	420
7/8-14	184	473	668
1-12	273	613	995
1-1/8-12	397	891	1445
1-1/4-12	553	1241	2012
1-3/8-12	746	1673	2712
1-1/2-12	978	2194	3557

Non-Standard



# 5030BU28

elasto-B-Mounts 50x30

50x30 B UNC3/8-16/28 NR 57 Shore

**Dimensions:**


D	H
50.00	30.00
G1	G2
UNC3/8-16	UNC3/8-16
L1	T
28.00	10.00
Elastomer	ShoreA
NR	57



**8. Torque Threaded Stud Test of elasto-A- and B-Mounts**

Tighten flat bar steel on jaw vise. Setup required torque wrench per table. Use a nut for specimen and tighten it with torque wrench until the required torque is achieved. Loosen nut from specimen and visual check threaded studs for:

- Stud extension
- Thread pitch damaged or sheered
- Connection between washer
- Broken stud







# 5030BU28

elasto-B-Mounts 50x30

50x30 B UNC3/8-16/28 NR 57 Shore

## Dimensions:

D	H
50.00	30.00
G1	G2
UNC3/8-16	UNC3/8-16
L1	T
28.00	10.00
Elastomer	ShoreA
NR	57



## 9. Certificate of RoHS Compliance

### Customer

**Philippe Skivee**

Spaenaur Inc.

815 Victoria Street North

Kitchener, Ontario N2G 4B1

We confirm that these mounts are RoHS Compliance.

## 9. Shelf Life Expectancy

Rubber to metal bonded products have a shelf life expectancy of up to 20 years under certain conditions such as room temperature and avoiding direct sunlight or artificial lights.

**- ALWAYS KEEP PARTS AWAY FROM DIRECT SUNLIGHT AND BETWEEN 10° - 30° CELSIUS -**